

MATERIAL DATA SHEET

Product **STAX steel fibers S205**

Material **low carbon steel**

Chem. Analysis (%)	C	max. 0,15
	Si	max. 0,30
	Mn	max. 1,20
	P	max. 0,05
	S	max. 0,05
	Fe	Rest

Short Fibers

Pour Volume: **155 – 165 ml / 100 g**
Glass cylinder, Ø 35 mm, 250 ml

Tap Volume: **90 – 120 ml / 100 g**
Tap volumeter Engelsmann, 2.000 strokes

Sieve Analysis:	1000 µm	max. 1 %
	500 µm	max. 5 %
	250 µm	10 – 20 %
	125 µm	15 – 30 %
	Pan	50 – 70 %

Fritsch, 10 min

Packaging: **Paper bags of 25 kg,**
Euro-pallets of 750 kg net/ IPPC-pallets of 1.000 kg

Marking: **Bag label**



Stand: C Datum: 13.05.2019 erstellt/ geändert: Inthirakumaran geprüft/ freigegeben: Gesell